

Patent  
Atty. Dkt. No. LYNN/0119

IN THE CLAIMS:

Please amend claims 34-37 and cancel claims 42 and 46 in accordance with the following replacement claim set:

1. (Previously Amended) A rubidium-82 generator, comprising:  
a strontium-82 support medium comprising sodium nonatitanate characterized by a strontium/rubidium separation factor greater than 12,500 at an alkaline pH.
2. (Original) The rubidium-82 generator of claim 1, wherein the sodium nonatitanate is characterized by a strontium selectivity greater than 250,000 mL/g at an alkaline pH.
3. (Original) The rubidium-82 generator of claim 1, wherein the sodium nonatitanate is characterized by a rubidium selectivity less than 100 mL/g at an alkaline pH.
4. (Canceled).
5. (Original) The rubidium-82 generator of claim 1, wherein the sodium nonatitanate is characterized by a strontium/rubidium separation factor greater than 100,000.
6. (Original) A process for preparing a rubidium-82 generator, comprising:
  - (a) preparing sodium nonatitanate from titanium isopropoxide and aqueous sodium hydroxide;
  - (b) heating the sodium nonatitanate at a temperature between 100°C and 250°C for a period between 12 hours and 2 weeks; and
  - (c) absorbing strontium-82 on the sodium nonatitanate from an aqueous solution comprising strontium-82 and sodium chloride, wherein the sodium chloride concentration is between 0.1 and 1 molar.
7. (Original) The process of claim 6, wherein the molar ratio of aqueous sodium hydroxide to

Patent  
Atty. Dkt. No. LYNN/0119

titanium isopropoxide is in excess of 0.44.

8. (Original) The process of claim 6, wherein the molar ratio of aqueous sodium hydroxide to titanium isopropoxide is between 2 and 6.

9. (Previously Amended) A method of chemically isolating strontium-82 from a proton-irradiated molybdenum target, comprising:

- (a) dissolving the molybdenum target containing the strontium-82;
- (b) adjusting the pH of the dissolved molybdenum target solution to an alkaline pH;
- (c) removing precipitates from the solution; and then
- (d) absorbing the strontium-82 from the solution onto a support comprising sodium

nonatitanate.

10. (Original) A process for preparing a solution containing rubidium-82, comprising:

- (a) providing a solution containing strontium-82 at a pH between 10 and 14;
- (b) absorbing strontium-82 onto a sodium nonatitanate support medium; and
- (c) eluting rubidium-82 from the sodium nonatitanate support medium with a solvent.

11. (Original) The process of claim 10, wherein the solvent is selected from the group consisting of water and saline solutions.

12. (Original) The process of claim 10, wherein the solvent is an aqueous solution having a sodium chloride concentration between 0.001 molar and 1 molar.

13. (Original) The process of claim 10, wherein the solvent is an aqueous solution having a sodium chloride concentration between 0.2 molar and 1 molar.

14. (Original) The process of claim 10, wherein the solvent is a pharmaceutical-grade saline and buffer solution.

Patent  
Atty. Dkt. No. LYNN/0119

15. (Original) A method of chemically isolating strontium-82 from a proton-irradiated rubidium or rubidium chloride target, comprising:
- (a) dissolving the target containing the strontium-82;
  - (b) adjusting the pH of the dissolved target solution to an alkaline pH;
  - (c) removing precipitates from the solution; and then
  - (d) absorbing the strontium-82 from the solution onto a support comprising sodium nonatitanate without absorbing rubidium.
16. (Previously Added) The rubidium-82 generator of claim 1, further comprising strontium-82 absorbed on the sodium nonatitanate.
17. (Previously Added) The rubidium-82 generator of claim 1, further comprising a sodium nonatitanate filter medium disposed to receive effluent from the strontium-82 support medium to trap strontium-82 leached from the generator.
18. (Previously Added) The rubidium-82 generator of claim 1, further comprising a column, wherein the sodium nonatitanate is disposed in the column.
19. (Previously Added) The rubidium-82 generator of claim 1, wherein the sodium nonatitanate is characterized by a strontium/rubidium separation factor greater than 59,200.
20. (Previously Added) The rubidium-82 generator of claim 1, wherein the sodium nonatitanate is characterized by a strontium/rubidium separation factor greater than or equal to 79,500.
21. (Previously Added) The process of claim 6, wherein the aqueous sodium hydroxide is about 50 wt% sodium hydroxide.
22. (Previously Added) The process of claim 6, further comprising:  
filtering the sodium nonatitanate from the solution.

Patent  
Atty. Dkt. No. LYNN/0119

23. (Previously Added) The process of claim 22, further comprising:  
washing the sodium nonatitanate with ethanol.
24. (Previously Added) The process of claim 23, further comprising:  
drying the sodium nonatitanate.
25. (Previously Added) The process of claim 6, wherein the molar ratio of aqueous sodium hydroxide to titanium isopropoxide is between 1 and 10.
26. (Previously Added) The process of claim 6, wherein the sodium nonatitanate is heated in a pressure vessel.
27. (Previously Added) The process of claim 6, wherein the sodium nonatitanate is prepared in the absence of chlorides and sulfates.
28. (Previously Added) The method of claim 9, wherein the molybdenum target is dissolved in hydrogen peroxide.
29. (Previously Added) The method of claim 9, wherein the pH is adjusted with sodium hydroxide.
30. (Previously Added) The method of claim 9, wherein the pH is adjusted to about 12.
31. (Previously Added) The method of claim 9, further comprising:  
stripping the strontium-82 from the sodium nonatitanate.
32. (Previously Added) The method of claim 31, wherein the strontium-82 is stripped from the sodium nonatitanate with mineral acid.
33. (Previously Added) The method of claim 9, further comprising:

Patent  
Atty. Dkt. No. LYNN/0119

washing the sodium nonatitanate with a buffer solution.

34. (Currently Amended) The process method of claim 9, wherein the sodium nonatitanate is characterized by a strontium/rubidium separation factor greater than 10,000.
35. (Currently Amended) The ~~rubidium-82 generator~~ method of claim 9, wherein the sodium nonatitanate is characterized by a strontium/rubidium separation factor greater than 12,500.
36. (Currently Amended) The ~~rubidium-82 generator~~ method of claim 9, wherein the sodium nonatitanate is characterized by a strontium/rubidium separation factor greater than or equal to 59,200.
37. (Currently Amended) The ~~rubidium-82 generator~~ method of claim 9, wherein the sodium nonatitanate is characterized by a strontium/rubidium separation factor greater than or equal to 100,000.
38. (Previously Added) The process of claim 10, wherein the sodium nonatitanate is characterized by a strontium/rubidium separation factor greater than 10,000.
39. (Previously Added) The rubidium-82 generator of claim 10, wherein the sodium nonatitanate is characterized by a strontium/rubidium separation factor greater than 12,500.
40. (Previously Added) The rubidium-82 generator of claim 10, wherein the sodium nonatitanate is characterized by a strontium/rubidium separation factor greater than or equal to 59,200.
41. (Previously Added) The rubidium-82 generator of claim 10, wherein the sodium nonatitanate is characterized by a strontium/rubidium separation factor greater than or equal to 100,000.
42. (Cancelled)

Patent-  
Atty. Dkt. No. LYNN/0119

43. (Previously Added) The process of claim 10, further comprising:  
disposing the sodium nonatitanate support medium into a column.
44. (Previously Added) The process of claim 10, wherein the solvent containing the eluted  
rubidium is alkaline.
45. (Previously Added) The process of claim 10, further comprising:  
buffering the solvent.
46. (Cancelled)
47. (Previously Added) The method of claim 15, wherein the dissolved target solution includes a  
buffer.
48. (Previously Added) The method of claim 47, wherein the buffer is an ammonia/ammonium  
chloride buffer.
49. (Previously Added) The method of claim 47, wherein the pH is between 9 and 10.
50. (Previously Added) The method of claim 15, wherein the pH is greater than 10.
51. (Previously Added) The method of claim 15, further comprising:  
stripping the strontium-82 from the sodium nonatitanate.
52. (Previously Added) The method of claim 51, wherein the strontium-82 is stripped from the  
sodium nonatitanate with mineral acid.
53. (Previously Added) The method of claim 15, further comprising:  
washing the sodium nonatitanate with a buffer solution.

Patent  
Atty. Dkt. No. LYNN/0119

54. (Previously Added) The process of claim 15, wherein the sodium nonatitanate is characterized by a strontium/rubidium separation factor greater than 10,000.

55. (Previously Added) The rubidium-82 generator of claim 15, wherein the sodium nonatitanate is characterized by a strontium/rubidium separation factor greater than 12,500.

56. (Previously Added) The rubidium-82 generator of claim 15, wherein the sodium nonatitanate is characterized by a strontium/rubidium separation factor greater than or equal to 59,200.

57. (Previously Added) The rubidium-82 generator of claim 15, wherein the sodium nonatitanate is characterized by a strontium/rubidium separation factor greater than or equal to 100,000.